

The right settings



SATA LM
2000 B RP

SATA Spray-
master RP

SATAjet
RP

2.0 mm nozzle
2 - 3 bar atomizing air
(26 - 42 psi)

SM Universal nozzle
0.5 - 0.8 bar paint cup
(7 - 14 psi)
1.5 - 2.5 bar atomizing air
(22 - 36 psi)

2.0 mm nozzle
2 bar atomizing air
(26 psi)

CRT White Basecoat
thinned with 10 - 20% distilled water

1.8 mm nozzle
2 - 3 bar atomizing air
(26 - 42 psi)

SM Universal nozzle
0.5 - 0.8 bar paint cup
(7 - 14 psi)
1.5 - 2.5 bar atomizing air
(22 - 36 psi)

1.8 mm nozzle
2 bar atomizing air
(26 psi)

CRT White Topcoat
thinned with 0 - 10% distilled water

1.8 - 2.0 mm nozzle
2 - 3 bar atomizing air
(26 - 42 psi)

SM Universal nozzle
0.5 - 0.8 bar paint cup
(7 - 14 psi)
1.5 - 2.5 bar atomizing air
(22 - 36 psi)

1.8 - 2.0 mm nozzle
2 bar atomizing air
(26 psi)

Digital Grey Lite Basecoat
Digital Grey Basecoat
thinned with 10 - 20% distilled water

1.6 - 1.8 mm nozzle
2 - 3 bar atomizing air
(26 - 42 psi)

SM Universal nozzle
0.5 - 0.8 bar paint cup
(7 - 14 psi)
1.5 - 2.5 bar atomizing air
(22 - 36 psi)

1.6 - 1.8 mm nozzle
2 bar atomizing air
(26 psi)

Digital Grey Lite Topcoat
Digital Grey Topcoat
Ultra Grey Topcoat
thinned with 0 - 5% distilled water

1.6 - 1.8 mm nozzle
2 - 3 bar atomizing air
(26 - 42 psi)

SM Universal nozzle
0.5 - 0.8 bar paint cup
(7 - 14 psi)
1.5 - 2.5 bar atomizing air
(22 - 36 psi)

1.6 - 1.8 mm nozzle
2 bar atomizing air
(26 psi)

Ultra Silver 3D Topcoat
thinned with 0 - 5% distilled water

1.8 - 2.0 mm nozzle
2 - 3 bar atomizing air
(26 - 42 psi)

SM Universal nozzle
0.5 - 0.8 bar paint cup
(7 - 14 psi)
1.5 - 2.5 bar atomizing air
(22 - 36 psi)

1.8 - 2.0 mm nozzle
2 bar atomizing air
(26 psi)

Rear Projection
thinned with 0 - 5% distilled water



SATA Farbspritztechnik GmbH & Co. KG
Domertalstraße 20
D-70806 Kornwestheim
Germany
www.sata.com